

RAPTOR



RFLPG/AL

RAPTOR Flame Proof Primer Grey



DESCRIPTION

A professional quality primer for use prior to the application of RAPTOR Flame Proof. Ideal for use on exhaust manifolds, headers, exhaust systems and other areas that require protection from very high heat. RAPTOR Flameproof Primer uses advanced ceramic technology that withstands temperatures up to 1000°C. When fully cured and used in combination with RAPTOR Flameproof, it provides a finish which is 5x tougher than ordinary paints with superior protection from heat, oil and other automotive fluids. It's easy to use and dries fast with excellent adhesion. Suitable for use on all types of metals including steel, aluminium, and alloys.

FEATURES

- Heat Resistant up to 1000°C
- Advanced Ceramic Technology (incorporates advanced heat-resistant pigment technology)
- Superior protection from heat, oil and other automotive fluids
- Excellent adhesion – won't blister, flake, crack or peel
- Clog Free Spot Nozzle – ideal for 3D surfaces
- 5x Tougher than ordinary paints

TECHNICAL DATA SHEET


RFLPG/AL

RAPTOR Flame Proof Primer Grey

Product preparation - application



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.




Direct to metal, bare steel, galvanised steel, aluminium, titanium, stainless steel, cured paint sanded with P180 and cleaned.
Clean and degrease. Mask any areas as required.
Thoroughly shake can for at least 2 mins before use.
Always wear safety goggles and gloves before spraying.
Use only outdoors or in a well-ventilated area.



Ready to use



Not applicable



2 - 3 coats sprayed 15 - 25cm away from the object

with intermediate flash-off: 10 min at 20°C
Handleable: 30 min at 20°C depending on film build
Sandable: 1 hr at 20°C depending on film build



Denib as required from P500 or scotch pad, then degrease, only use waterbased degreaser applied to the cloth to avoid soaking of the surface

VOC compliant

2004/42/IB/e(840) 719: The EU limit value for this product (product category: e) in ready to use form is maximum 840 g/l of VOC. The VOC content of this product in ready to use form is maximum 719 g/l.

TECHNICAL DATA SHEET

RFLPG/AL


RAPTOR Flame Proof Primer Grey

Products


RAPTOR® Flame Proof Primer Grey



25 - 35 µm 2 coats



RAPTOR® Flame Proof Primer Grey can be overcoated with itself within 12 hours, without sanding, after this time abrade with P500, clean with waterbased degreaser then apply RAPTOR Flameproof colour coat or RAPTOR Flameproof Primer if substrate is showing through.



After use, hold aerosol can upside down and spray briefly to clean nozzle. If the nozzle becomes blocked, remove from the can and soak in gentle thinners before replacing. Do not stick pins into the orifice.

Waste treatment

Dispose of contents and container in accordance with all local, regional, national and international regulations.

Remarks

- Theoretical coverage 1m² per unit, assuming 100% transfer efficiency and at the indicated film build.
- NOTE: There is no need to cure between primer, topcoat and clearcoat but it is needed after the full system is applied.
- If you want to overcoat after curing the coating, abrade with P180 and touch up with primer if substrate is showing through.
- Aerosol cans should be stored for 2 hours at room temperature before use. For long term storage keep in a dry well ventilated area and away from direct sunlight and frost. Recommended storage temperature 5 - 25°C, recommended application temperature 20°C

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our brand product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our brand product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.