

RAPTOR[®]

TOUGH PROTECTIVE COATINGS



Products you will need



HOW TO ACHIEVE GREY SHADES MIXING BLACK AND WHITE KITS

- 1**

PLACE EMPTY CUP
Place the empty mixing cup on the scale.
- 2**

SHAKE
Shake RAPTOR White and Black bottles for 2 mins.
- 3**

MEASURE BY WEIGHT
Measure the required amounts of black and white RAPTOR into the mixing cup by weight for colour consistency.
- 4**

MIX
Mix thoroughly.
- 5**

ADD HARDENER
Introduce the hardener to the mix and mix all together for 2 mins.
- 6**

RETURN TO BOTTLE
Once thoroughly mixed, return to the bottle.
- 7**

APPLY RAPTOR
You are now ready to shoot RAPTOR.

TOP TIPS:

| | |
|--------------------|--------|
| White | |
| 100% White | 850g |
| Barely Grey | |
| 90% White | 765g |
| 10% Black | 85g |
| Light Grey | |
| 80% White | 680g |
| 20% Black | 170g |
| Grey | |
| 70% White | 595g |
| 30% Black | 255g |
| Dark Grey | |
| 25% White | 212.5g |
| 75% Black | 637.5g |
| Black | |
| 100% Black | 850g |

NOTES:

ALL KITS COME WITH THE CORRECT HARDENER TO RAPTOR RATIO, FOR CORRECT ACTIVATION. CORRECT MEASURING IS CRUCIAL. WE RECOMMEND TINTING OUT OF THE BOTTLE TO ENSURE THOROUGH MIXING.

WWW.RAPTORCOATINGS.COM

U-POL Ltd, 4th Floor, The Grange, 100 High Street, London N14 6BN.

T: +44 (0)20 8492 5900 E: uk.sales@u-pol.com

U-POL TECHNICAL SUPPORT:

+44 (0) 1933 230310